

MIL-B-2427G (AR)
AMENDMENT 4
14 July 1989

SUPERSEDING
AMENDMENT 3
11 May 1988

MILITARY SPECIFICATION

BOX, AMMUNITION PACKING: WOOD, NAILED

This Amendment forms a part of Military Specification MIL-B-2427G (AR), dated 30 August 1984, and is approved for use within the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

2.1.1 Specifications and Standards: Under STANDARDS,
MILITARY, delete:

"MS 35492 - Screw, Wood, Flat Head, Cross Recessed
MS 35494 - Screw, Wood, Flat Head".

PAGE 8

3.3 Rope handles. After the third sentence, add:

"This length is the length of exposed rope. It does not include the length of rope needed for attachment to the box (i.e., that length attached to the cleats). This adds approximately six inches of rope."

PAGE 9

3.4 Metal fittings. Delete the following drawings listed:

"MS 35492 - Screw, Wood, Flat Head, Cross Recessed, Part
Number (No.) MS-35492-41
MS 35494 - Screw, Wood, Flat Head, Part Number (No.)
MS-35494-46"

MIL-B-2427G (AR)
AMENDMENT 4

Last sentence: Delete in its entirety and substitute:

"Screws shall be standard commercial number 8 x 3/4 inch steel, tamperproof wood or sheet metal screws of the one-way drive variety. The screws shall be cadmium or zinc coated. The screw shall meet all requirements of FF-S-107 except for head design."

PAGE 12

3.7.1 Tenth sentence: Delete "more than 1/8 the thickness of the board" and substitute "more than .125 inches below board surface".

3.7.1 After last sentence, add sentence as follows:

"When two nails are occasionally driven coincidentally in the same location, the nails shall be acceptable as long as the integrity of the box is not affected (splitting terminating in edge of box)."

PAGE 13

3.8 Box identification. After the third sentence, add:

"The letters "PC" shall be annotated on all boxes subjected to either the Cunapsol 5 (copper naphthenate) or the M-GARD W510 (copper naphthenate) preservative in accordance with 3.9."

PAGE 14

3.9 Preservative treatment. Delete in its entirety and substitute:

"3.9 Preservative treatment. Grade A boxes, or the finished wood parts thereof, shall be completely immersed for a minimum of one minute with any of the following wood preservatives:

- a. A solution of PQ56 reduced with water down to 1.8 percent copper-8-quinolinolate as solution (see 6.6).
- b. An emulsion of wood preservative M-GARD W550 (zinc naphthenate) reduced with water down to 3 percent zinc as metal (see 6.7).

MIL-B-2427G (AR)
AMENDMENT 4

- c. An emulsion of M-GARD W510 (copper naphthenate) reduced with water down to 2 percent copper as metal (see 6.14).
- d. A solution of Cunapsol 5 (copper naphthenate) reduced down with water down to 2 percent copper as metal (see 6.15).

Alternately, Grade A boxes or the finished wood parts thereof shall be completely flooded for a minimum of one minute in PQ 56, M-GARD W550, M-GARD W510 or Cunapsol 5 preservative, as applicable, as to inundate all interior and exterior surfaces (when finished wood parts are dipped). Care shall be exercised to assure complete coverage of all surfaces of the board. After the dip treatment, the boxes must be air dried (or dried for an appropriate time in a kiln or oven) for a period of 24 hours minimum in a well ventilated area allowing full air circulation around all surfaces of the wood box. The boxes must be dried prior to shipment.

The box manufacturer will be required to obtain and provide all available safety, health and environmental data, i.e., EPA Hazard Data Sheets, OSHA Safety Data Sheets, etc. Of specific interest are the acute, subchronic and chronic toxicity data. Also, the manufacturer will obtain and provide any special safety, health and environmental information (apparatus and procedures) to be used throughout the treated box duty life and disposal.

3.9.1 Presence of PQ 56 (copper-8-quinolinolate) preservative. When treated with PQ56, the box shall show evidence of discoloration when tested as specified in 4.5.5.

3.9.2 Presence of M-GARD W550 (zinc naphthenate emulsifiable) preservative. When treated with M-GARD W550, the box shall show evidence of discoloration when treated as specified in 4.5.6.

3.9.3 Presence of M-GARD W510 (copper naphthenate) or Cunapsol 5 (copper naphthenate) preservative. When treated with M-GARD W510 or Cunapsol 5, the box shall show evidence of discoloration when treated as specified in 4.5.7."

4.4.3.5 and 4.4.3.6 Delete in their entirety and substitute:

"4.3.3.5 Presence of wood preservative. (see 3.9), Major defect. A sample of 15 boxes shall be selected at random, from each lot, for this test. Four individual boards of each box (cleat, top or bottom board, end board and batten) shall be subjected to the test specified in 4.5.5, 4.5.6, or 4.5.7, as applicable. If one or more boards fail to meet the applicable requirement, the box shall be classed defective. Failure of any box to comply with the requirements shall be cause for rejection of the lot."

* 4.5.1 Load test of rope handles. Delete in its entirety and substitute the following paragraphs:

"4.5.1 Load test of rope handles. The box shall be packed with any suitable material until its gross weight is twice as great as its gross weight packed with the item for which it was intended. If the resulting weight of the packed box is 250 pounds (lbs.) or less, 4.5.1.1 shall be followed. If the resulting weight is greater than 250 lbs. and not greater than 500 lbs., 4.5.1.2 shall be followed.

4.5.1.1 Rope handle load test (250 lbs. or less). The box shall be suspended freely for one minute, minimum, from each rope handle in turn. In the event that one or both handles fail the requirement, the box shall be classed defective.

4.5.1.2 Rope handle load test (from greater than 250 lbs. to 500 lbs., maximum). The box shall suspend freely, for one minute, minimum, from both rope handles (at once). In the event that one or both handles fail the requirement, the box shall be classed defective."

4.5.6 Presence of M-GARD W550 (zinc naphthenate emulsifiable) preservative: Delete in its entirety and substitute:

"4.5.6 Presence of M-GARD W550 (zinc naphthenate emulsifiable) preservative.

MIL-B-2427G (AR)
AMENDMENT 4

4.5.6.1 Materials and equipment. The materials and equipment required are as follows:

- a. Reagent. Dissolve 0.1 grams of dithizone (diphenylthiocarbazon) (see 6.12) in either 100 ml of methyl ethyl ketone or 100 ml of chloroform. (Note: This solution may be stored for long periods of time.)
- b. Eye dropper. An ordinary glass tube eyedropper may be used.

4.5.6.2 Test procedure. Five drops of the solution shall be applied to the wood surface. The indicator will turn red when zinc (M-GARD W550) is present. The color green indicates that the preservative is not present. Both colors fade quickly in the presence of light."

PAGE 23

After 4.5.6.2.2 Test procedure. add new paragraphs as follows:

"4.5.7 Presence of M-GARD W510 (copper naphthenate emulsifiable) or Cunapsol 5 (copper naphthenate) preservative. The materials and equipment required are as follows:

- a. Reagent. Dissolve 0.5 grams chrome azurol "S" concentrate (see 6.11) and 5.0 grams sodium acetate in 80 ml of distilled water and then dilute further to 500 ml total with distilled water.
- b. Sprayer. A common manual (fly) sprayer type applicator shall be used.

4.5.7.1 Test procedure. Spray solution over surface of dried treated wood. A deep blue color reveals the presence of copper (from copper naphthenate)."

PAGE 26

6.12 Change to read as follows:

"6.12 Dithizone. Dithizone (diphenylthiocarbazon) may be obtained from J. T. Baker Chemical Co., Phillisburg, New Jersey 08865 or equivalent facility."

MIL-B-2427G (AR)
AMENDMENT 4

Add new paragraphs as follows:

"6.14 M-GARD W510. M-GARD W510 (copper naphthenate), for 2 percent copper as metal, may be obtained from Mooney Chemicals Inc., 2301 Scranton Road, Cleveland, Ohio 44113-9988 or equivalent facility.

6.15 Cunapsol 5. Cunapsol 5 (copper naphthenate), for 2 percent copper as metal, may be obtained from Chapman Chemical Company, P.O. Box 9158, Memphis, TN 38019 or equivalent facility."

The margins of this amendment are marked with an asterisk or vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 8140-A790)